



HYDROSTOP WS10

HYDROPHILIC RUBBER WATERSTOP

DESCRIPTION

HYDROSTOP WS10 is swellable hydrophilic waterstop which will swell upon contact with water. When installed into a confined joint the expansion of the waterstop exerts a positive pressure against both faces of the concrete to achieve a watertight seal which is resistant to hydraulic pressure. HYDROSTOP WS10 will swell up to 200% which makes it particularly suitable for sealing smaller sections of concrete. The installed waterstop has a delayed initial swell which prevents premature swell.

USES

HYDROSTOP WS10 is designed for use in both horizontal and vertical construction joints in cast in-situ concrete. It may also be used for the sealing of joints between pre-cast elements however care should be taken to ensure that the waterstop is in proper contact with the concrete elements. HYDROSTOP WS10 is used for sealing construction joints where resistance to hydrostatic water pressure is required to achieve a watertight structure. Such applications include, basement construction, culverts, tunnels, retaining walls, lift pits and other water resisting structures.

ADVANTAGES

- Easy application to complex shapes, due to small dimension.
- Good swell capacity upon contact with water.
- Delayed swell composition.
- Suitable for use in conjunction with HYDROBAR PVC waterstops.
- Design life at least equal to that of the structure where it is incorporated.

Property	Value
Application Temperature	6°C to 30°C
Working life	50 mins @ 20°C
Application Thickness	10 to 80mm
Compressive Strength	21MPa @ 1 day 40MPa @ 7 days 48MPa @ 28 days
Water Permeability Coefficient	5.98×10^{-15} m/sec
Oxygen Diffusion Coefficient	2.65×10^{-4} cm ² /sec

HYDROSTOP WS10

HYDROPHILIC RUBBER WATERSTOP

PROCEDURE

Surface Preparation: The substrate to which the HYDROSTOP WS10 is to be applied, should be clean, dry and free from deleterious materials. The surface should be smooth and free from excessive surface undulation. Installation during heavy rain is not recommended as this may cause premature activation of the waterstop. The surface of the joint should be scabbled prior to the application of the waterstop.

Application: HYDROSTOP WS10 should be applied to the substrate using HYDROSTOP WSM as an adhesive. Apply a 10mm bead to the concrete and press the waterstop firmly into the HYDROSTOP WSM ensuring complete contact with the adhesive. HYDROSTOP WS10 should be nailed at 300mm centres using HYDROSTOP RETAINING PINS. Adjacent strips of HYDROSTOP WS10 should be parallel lapped by 100mm to ensure a complete seal is achieved. Internal and external corners should be formed by cutting the HYDROSTOP WS10 and butt jointing. Do not bend the HYDROSTOP WS10 around corners, as this will affect the integrity of the seal achieved. Allow the HYDROSTOP WSM adhesive to cure overnight before subsequent concrete pour.

It is important to ensure that the HYDROSTOP WS10 is positioned so that there is at least 50mm concrete cover. The installed HYDROSTOP WS10 should be protected from rain damage until the concrete is placed. It is extremely important that when the concrete is placed it is well compacted around the waterstop, as any voids will allow the water to track around the installed waterstop.

LIMITATIONS

HYDROSTOP WS10 should not be installed in movement or expansion joints.

PACKAGING & COVERAGE

Pack Size:
HYDROSTOP WS10 is supplied in a 3mm x 20mm x 12m roll.

STORAGE & SHELF LIFE

It is important to ensure that HYDROSTOP WS10 is protected from wet conditions when stored in unopened containers. It will have a shelf life in excess of 1 year.

HEALTH & SAFETY

See separate material safety datasheet.



Premcrete Ltd | Reg no. 08079452 VAT no. 194306207

Structural Waterproofing | Gas Protection
| Concrete Repair Technical Grouts | Joint
Sealants | Protective Coatings | Admixtures

www.premcrete.com | 02380 276166 |
sales@premcrete.com | 44 Macadam Way,
West Portway, Andover, Hampshire, SP10
3XW

The information provided in this data sheet is intended for general guidance only and is given in good faith based on Premcrete Ltd current knowledge and experience. No warranty in respect of fitness for a purpose, or any other liability whatsoever can be inferred from the information contained within this datasheet. Users should determine the suitability of the materials for their particular application and should always refer to the most recent issue of the product data sheet for the product concerned. All materials are supplied in accordance with Premcrete Ltd Sales Terms & Conditions (available upon request and on Company Website).