



HYDROSTOP WSM

HYDROPHILIC MASTIC SEALANT

DESCRIPTION

HYDROSTOP WSM is a gun-applied mastic sealant for application where a swellable mastic is required to provide an effective watertight seal in confined applications. The hydrophilic properties of HYDROSTOP WSM display good consistency in swell rate during repeated wet/dry cycles. When it is confined by concrete it will create a positive pressure against the face of the concrete joint which will prevent the passage of water.

USES

HYDROSTOP WSM is used as an adhesive for bonding HYDROSTOP BR to concrete substrate. It is also used as a hydrophilic sealant for providing an effective seal in difficult areas which preclude the use of the hydrophilic water stop. It is used for sealing around pre-cast segments, metal beams, service penetrations and as an effective mastic for the bonding of HYDROSTOP BR to HYDROBAR PVC WATERSTOPS.

ADVANTAGES

- Provides an effective seal to a variety of substrates.
- Swells in excess of 200 % to produce a water tight seal.
- Durable performance for the life time of the structure.
- Fast curing enabling concrete to be placed within 24 hr.
- Good adhesion to a variety of substrates.
- Design life at least equal to that of the structure where it is incorporated.

Property	Value
Colour	Grey
Hardness Shore A	30
Cure Rate	3mm / 24 hr
Swell Ratio	200%

PROCEDURE

Surface Preparation: The surface to which the HYDROSTOP WSM is to be applied should be free from all loose material. The substrate should be relatively smooth. HYDROSTOP WSM may be applied to damp concrete however no surface water should be present.

Application: HYDROSTOP WSM is applied in a foil sachet which may be fitted into a bulk sealant gun. The foil sachet should be cut before applying as a traditional sealant. Where the HYDROSTOP WSM is to be used as an adhesive for the HYDRSTOP BR a minimum 10mm bead should be applied to embed the water bar into. Where the HYDROSTOP WSM is to be used to provide an effective seal in its own right, then a 15mm diameter bead should be extruded onto the substrate, ensuring there is no break in the bead.

LIMITATIONS

HYDROSTOP WSM should not be used for expansion joints or joints where significant repetitive movement is expected. HYDROSTOP WSM should only be used where there is more than 75mm concrete cover. HYDROSTOP WSM should not be used as a sealant in general building applications.



PACKAGING & COVERAGE

Pack Size: 600ml

Coverage: A 600ml sachet will extrude a 2.7m bead at 15mm diameter.

STORAGE & SHELF LIFE

HYDROSTOP WSM should be stored in clean dry conditions at temperatures between 8°C and 25°C.

HEALTH & SAFETY

See separate material safety datasheet.



Premcrete Ltd | Reg no. 08079452 VAT no. 194306207

Structural Waterproofing | Gas Protection
| Concrete Repair Technical Grouts | Joint
Sealants | Protective Coatings | Admixtures

www.premcrete.com | 02380 276166 |
sales@premcrete.com | 44 Macadam Way,
West Portway, Andover, Hampshire, SP10
3XW

The information provided in this data sheet is intended for general guidance only and is given in good faith based on Premcrete Ltd current knowledge and experience. No warranty in respect of fitness for a purpose, or any other liability whatsoever can be inferred from the information contained within this datasheet. Users should determine the suitability of the materials for their particular application and should always refer to the most recent issue of the product data sheet for the product concerned. All materials are supplied in accordance with Premcrete Ltd Sales Terms & Conditions (available upon request and on Company Website).