



TEKNOCEM HBR

HIGH-BUILD STRUCTURAL MORTAR

DESCRIPTION

TEKNOCEM HBR is a polymer-modified fibre reinforced cementitious repair mortar. The mortar incorporates shrinkage compensating additives making it suitable for structural repair applications. The mortar can be applied to vertical and overhead substrates and is easily finished using a steel trowel to obtain a fair faced appearance. The mortar consists of a unique blend of lightweight fillers which enable effective high-build repairs to be carried out on vertical and overhead applications without the freshly placed mortar slumping. TEKNOCEM HBR is chloride free making it suitable for application where steel reinforcement is present. The hardened mortar possesses low absorption properties offering good resistance to the effects of freeze-thaw action.

USES

TEKNOCEM HBR is used for the repair and reinstatement of structural concrete where a high-build mortar is required for application to vertical and overhead substrates. Its high strength properties make it suitable for the repair of structural elements and where high early strengths are required.

Property	Value
Compressive Strength	18MPa @ 1 Day 30MPa @ 7 Days 44MPa @ 28 Days
Tensile Strength	2.8 MPa @ 28 Days
Flexural Strength	6 MPa @ 28 Days
Density	1710Kg/ m ³
Working Life	Approximately 20mins @ 20°C
BS EN 1504-3 Compliant	R3

PROCEDURE

Surface Preparation: The perimeter of the repair should be saw cut to a depth of 10mm and all loose and damaged concrete should be carefully removed back to sound substrate. Any steel reinforcement within the repair area should be fully exposed around the full circumference of the bar. Exposed steel should be cleaned back to clean bright steel by means of grinding or grit blasting. Any surface contaminants should be removed by suitable means to ensure a good quality clean substrate that has a strength in excess of 20 MPa.

Substrate Priming: Typically, substrates do not require the use of a separate substrate primer, the substrate should just be fully saturated with water, taking special care to ensure no standing water is present before application of the mortar. Particularly porous substrates may require the use of TEKNOPRIME 842. Exposed steel reinforcement should be primed using TEKNOPRIME 841.

Mixing: TEKNOCEM HBR should be mixed using a forced action paddle mixer or pan mixer. Clean water should be poured into the mixing vessel at a rate of 3.75 litres depending on the desired consistency. The mortar should be mixed until a uniform homogenous mix is achieved. Once mixing is complete the mortar application should begin immediately to ensure maximum workability of the mortar.

Application: TEKNOCEM HBR can be trowel applied as a render, once a good contact coat has been applied to the substrate. Obtaining a good contact coat to the sub-base is essential to ensure the cohesion of the mortar once placed, particularly in vertical and overhead situations. If repairs are to be carried out around rebar, then it is important to hand place the mortar to ensure good compaction around the rebar without any voids. The mortar can be placed in thicknesses between 10mm and 50mm, without the need for

shuttering, however support may be required depending on the exact profile that is to be achieved. In thicker sections the mortar may be placed in layers, ensuring that each layer is firm and stable, and a keyed surface has been provided before adding the next layer.

Curing: Once placed the TEKNOCEM HBR should be cured in accordance with standard concreting practices. The surface should be cured using CUREAID AC to prevent shrinkage cracking occurring. The freshly applied mortar should be protected from strong, direct sunlight using suitable sheeting.

PACKAGING & COVERAGE

Pack Size: 25kg

Yield: 14.5ltrs per 25kg pack.

Coverage: A 25kg bag will cover 1.4m²
@ 10mm thickness.

STORAGE & SHELF LIFE

TEKNOCEM HBR should be kept in clean dry conditions at temperatures between 8°C and 30°C. When stored in unopened bags, the product will have a shelf life of 12 months.

HEALTH & SAFETY

See separate material safety datasheet.



Premcrete Ltd | Reg no. 08079452 VAT no. 194306207

Structural Waterproofing | Gas Protection
| Concrete Repair Technical Grouts | Joint
Sealants | Protective Coatings | Admixtures

www.premcrete.com | 02380 276166 |
sales@premcrete.com | 44 Macadam Way,
West Portway, Andover, Hampshire, SP10
3XW

The information provided in this data sheet is intended for general guidance only and is given in good faith based on Premcrete Ltd current knowledge and experience. No warranty in respect of fitness for a purpose, or any other liability whatsoever can be inferred from the information contained within this datasheet. Users should determine the suitability of the materials for their particular application and should always refer to the most recent issue of the product data sheet for the product concerned. All materials are supplied in accordance with Premcrete Ltd Sales Terms & Conditions (available upon request and on Company Website).